


WhiteOptics® White 98 Film


Part Code: F16-98

Descriptor: High diffuse reflectance film, matte finish

Options: Available on a roll or as custom die-cut parts Available with or without adhesive backing



Optical



Mechanical/Thermal

Properties	Value	Method
Reflectance at 550nm	97.5 ± 0.8%	ASTM E1164
L* value	> 98.9	ASTM E308
a value	-0.35 ± 0.25	ASTM E308
b value	0.90 ± 0.30	ASTM E308
Gloss (60 degree)	<5.0%	ASTM D2456

Properties	Value	Method
Thickness (microns)	205 ± 15	Ono Sokki EG225
Tensile Strength (MPa)	165	ASTM D882
Deformation Temperature (C)	130	JIS K7196-1991
Melt Temperature (C)	255	ASTM D3418
UL Relative Thermal Index (C)	105	UL746

- UV stable for most applications
- Continuous thermal stability up to 100°C
- Stable in humid environments
- Anti-static, does not attract dust
- Abrasion resistant
- Compatible with most common cleaning solutions including dilute ammonia, soap solutions, Clorox® wipes, Pine-sol®, Formula 409® and dilute bleach



WhiteOptics LLC
243-G Quigley Blvd.
New Castle, DE 19720



inquiries@whiteoptics.com
whiteoptics.com



302-476-2055

